


# CIPTEX™ 9320

## Polyisocyanurate Foam



### Products Description

CIPTEX 9320 is a foaming material made of isocyanate reacted with polyether after catalysis. Its physical and fireproofing properties is superior to general polyurethane. It is the ideal cryogenic insulation material with low thermal conductivity, good anti-vibrational characteristic and strong adaptability.

CIPTEX 9320 meets ASTM and GB industry standard.

### Density Range

- 320±20 kg/m<sup>3</sup>

### Specification

- High closed cell content
- Good pressure and flexure resistance
- Excellent cryogenic insulation
- Good flame retardancy

### Application

- Insulated piping in Lng station
- Cryogenic insulation in freezer and central air conditioning system

### CIPTEX 9320 PHYSICAL PROPERITIRS

Appearance		Yellowish foam
HCFC	(QB/T5114-2017)	No
Thermal Conductivity	(GB/T10295-2008/ ASTM C 518)	0.0493 W/(m.k)
Water Absorption	(GB/T8810-2005/ ASTM D 2842)	1.2 %
Closed Cell Content	(GB/T10799-2008/ ASTM D 2856 )	>95 %
Compressive Strength	(GB/T 8813-2008/ ASTM D 1621)	8.12 MPa
Oxygen Index	(GB/T 2406.2-2009)	28.4%

---

**Instruction**

This data, while believed to be accurate and based on reliable analytical methods, is for informational purposes only. The terms and conditions of the agreement under which it is sold will govern any sales of this product. Data supplied above are "typical values"; not to be considered "specification values". To assure the material's performance is adequate for a specific application; customers should verify, independent of Herence, performance characteristics of interest.

---

**Contact**

Herence New Material Technology Co.,Ltd  
No 15, Shangde Road, Xuejia Town, Xinbei District,  
Changzhou, Jiangsu Province, 213000,P.R.China

[www.herence.cn](http://www.herence.cn)

**Disclaimer**

The Herence New Material logo, Herence™ and all products denoted with ™ or ® are trademarks or registered trademarks of Herence New Material and its affiliates. Herence New Material trademarks may not be used in connection with any product or service that is not a Herence product or service.

Copyright © 2018 Herence New Material Technology Co., Ltd.